

Chemical and Physical Analysis of Fly Ash

Developed For: *Headwaters Resources*
 16817 - 155th PI SE
 Renton, WA 98058


Ticket: 9119 Job: 14708 Report Date: 05/28/2009	Plant of Origin: <i>Centralia US</i> Sample ID: <i>Ce-020-09</i> Docket: 3030887 - 3030963	Sample Date Range: 04/13/2009 to: 04/16/2009 Date Received: 04/22/2009
---	--	--

Chemical Composition (%) <small>(by Wyoming Analytical Laboratories, Inc.)</small>	CSA A3000-08 Specifications	
	<u>Class F</u>	<u>Class CI</u>
Total Silica, Aluminum, Iron:	69.9	
Silicon Dioxide:	47.1	
Aluminum Oxide:	16.8	
Iron Oxide:	6.1	
Sulfur Trioxide:	1.0	5.0 Max
Calcium Oxide:	16.9	8 Max
Moisture Content:	0.0	3.0 Max
Loss on Ignition:	0.1	8.0 Max

Physical Test Results	CSA A3000-08 Specifications	
	<u>Class F</u>	<u>Class CI</u>
Fineness, Retained on #325 Sieve (%):	18.3	34 Max
Optional Strength Activity Index (%)		
ASTM C-311 (28 Days @ 23 C):	105.7	75 Min
Water Requirement, % of Control:	93.4	
Soundness, Autoclave Expansion (%):	0.02	0.8 Max
Density Mg/m ³ :	2.63	

Comments:

CTL | Thompson Materials Engineers, Inc.



Orville R. Werner II, P.E.

