

## MILL TEST REPORT

Cement Type: **CSA Type GU**  
**Low Alkali Portland Cement**

Plant: **Delta, BC**

<b>Certificate #:</b>	<b>D1-370</b>
-----------------------	---------------

Production Period:	Feb 01 2009 Feb 28 2009	Test Result	CSA A3001 Specification
SiO2 (%)	CSA A3003	19.9	-
Al2O3 (%)	CSA A3003	5.12	-
Fe2O3 (%)	CSA A3003	3.68	-
CaO (%)	CSA A3003	64.6	-
MgO (%)	CSA A3003	0.85	max. 5.0
SO3 (%)	CSA A3003	2.80	max. 3.0
Na2O (%)	CSA A3003	0.29	-
K2O (%)	CSA A3003	0.34	-
TiO2 (%)	CSA A3003	0.27	-
C3S (%)	ASTM C150	64	-
C2S (%)	ASTM C150	9	-
C3A (%)	CSA A3003	7.3	-
C4AF (%)	ASTM C150	11.2	-
Equivalent Alkalies (%)	ASTM C150	0.51	-
Loss on Ignition (%)	CSA A3003	2.5	max. 3.0
Insoluble Residue (%)	CSA A3003	0.12	max. 1.5
Free Calcium Oxide (%)	CSA A3003	0.32	-
<b>Vicat Setting Time</b>			
Initial (minutes)	CSA A3004-B2	122	min. 45 max. 360
Final (minutes)	CSA A3004-B2	230	-
<b>Blaine Fineness (m2/kg)</b>	ASTM C204	389	-
+325 mesh	CSA A3004-A3	1.1	max. 28
<b>Air Content (%)</b>	CSA A3004-C4	6.37	-
<b>Autoclave Expansion (%)</b>	CSA A3004-B5	0.00	max. 1.0
<b>Compressive Strength</b>		<b>MPa / psi</b>	
3 Day	CSA A3004-C2	29.2 / 4229	min. 14.5
7 Day	CSA A3004-C2	37.4 / 5418	min. 20.0
28 Day (previous month)	CSA A3004-C2	47.5 / 6894	min. 26.5

This will certify that the above described cement meets the standard chemical and physical requirements of CSA Specification A3001-08 for Type GU Portland Cement.

