

MILL TEST REPORT

Cement Type: **CSA Type GU**
Low Alkali Portland Cement

Plant: **Delta, BC**

Certificate #:	D1-379
-----------------------	---------------

Production Period:	Nov 01 2009 Nov 30 2009	Test Result	CSA A3001 Specification
SiO2 (%)	CSA A3003	19.8	-
Al2O3 (%)	CSA A3003	5.09	-
Fe2O3 (%)	CSA A3003	3.79	-
CaO (%)	CSA A3003	64.9	-
MgO (%)	CSA A3003	0.83	max. 5.0
SO3 (%)	CSA A3003	2.83	max. 3.0
Na2O (%)	CSA A3003	0.34	-
K2O (%)	CSA A3003	0.37	-
TiO2 (%)	CSA A3003	0.24	-
C3S (%)	ASTM C150	66	-
C2S (%)	ASTM C150	7	-
C3A (%)	CSA A3003	7.1	-
C4AF (%)	ASTM C150	11.5	-
Equivalent Alkalies (%)	ASTM C150	0.58	-
Loss on Ignition (%)	CSA A3003	2.7	max. 3.0
Insoluble Residue (%)	CSA A3003	0.28	max. 1.5
Free Calcium Oxide (%)	CSA A3003	0.48	-
Vicat Setting Time			
Initial (minutes)	CSA A3004-B2	107	min. 45 max. 375
Final (minutes)	CSA A3004-B2	213	-
Blaine Fineness (m2/kg)	ASTM C204	398	-
+325 mesh	CSA A3004-A3	1.4	max. 28
Air Content (%)	CSA A3004-C4	6.47	-
Autoclave Expansion (%)	CSA A3004-B5	0.00	max. 1.0
Compressive Strength		MPa / psi	
3 Day	CSA A3004-C2	31.3 / 4543	min. 14.5
7 Day	CSA A3004-C2	37.8 / 5486	min. 20.0
28 Day (previous month)	CSA A3004-C2	45.8 / 6646	min. 26.5

This will certify that the above described cement meets the standard chemical and physical requirements of CSA Specification A3001-08 for Type GU Portland Cement.

